



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 14.5x2.4 - FFKM - FFPM - Hohe Temp - 75 Shore A - Schwarz -

<https://www.o-ring-stocks.eu/de/o-ring-14.5x2.4-ffkm-ffpm-hohe-temp-75-shore-a-schwarz-kalrez-4079-ors71797-gleichwertig>

Specificaties

Productnummer	71797
Merk	Eurolast
Categorie	FFKM O-Ringe- 75 Shore A - F758Z96
Materiaal	FFKM - FFPM
Kleur	Zwart
Farbe	Black

Kernspezifikationen

Genehmigung	General Purpose (+330°C)
-------------	--------------------------

Alternativer Name	FFPM – Dupont Kalrez
Chemischer Name	Perfluoroelastomer
Description 2	O-ring FFKM - FFPM 14.5x2.4
Equal to	Dupont Kalrez® 4079 - Greene Tweed Chemraz® 615 - PPE Perlast® G75B - Trelleborg Isolast® J8325 & Isolast® J9876
Größe im Text	fourteen comma fifty by two comma forty
Markennamen	Kalrez® - Simriz® - Chemraz® - Spectrum® - Triazinico® - Isolast® - Parofluor® - Fluorez® - Perlast® - Perfluor®
Material	FFKM - FFPM
Packungseinheit	O-ring
Produkte name	O-ring 354x3.5 FFKM

Alternative Größe

DIN 3771 Größentabelle	14.5x2.4
JIS B 2401 Größentabelle	JIS P15
SMS 1586 Größentabelle	14.5 X 2.4

Gleichwertig an

Dupont Kalrez® Äquivalent	Dupont Kalrez® 4079
Greene Tweed Chemraz® Äquivalent	Greene Tweed Chemraz® 615
Precision Polymer Engineering Perlast® Äquivalent	PPE Perlast® G75B
Trelleborg Isolast® Äquivalent	Trelleborg Isolast® J8325 & Isolast® J9876

Kernspezifikationen

CS (Schnur Starke)	2.4 mm
--------------------	--------

Specificaties

Härte	75 Shore A
ID (Inner Durchmesser)	14.5 mm
Temperatur Max	330 °C
Temperatur Min	-15 °C