



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 158.35x3.53 - ACM - 70 Shore A - Noir - ORS35501

<https://www.o-ring-stocks.eu/fr/joint-torique-158.35x3.53-acm-70-shore-a-noir-ors35501>

Specificaties

Productnummer 35501

Merk Eurolast

Categorie ACM O-Rings

Materiaal ACM

Kleur Zwart

Kleur Black

Basis Specificaties

Keurmerk None

Chemische Benaming PolyAcrylate Rubber / alkyl acrylate copolymer

Extra omschrijving O-ring 158.35x3.53 ACM

Maat in tekst one hundred and fifty eight comma thirty five by three comma fifty three

Materiaal ACM

Merkenamen HyTemp

Omschrijving-2 O-ring ACM 158.35x3.53

Verpakkingseenheid O-ring

Alternative maat

AS568 Maat AS 259

DIN 3771 Maat 158.35x3.53

SMS 1586 Maat 158.35 X 3.53

Basis Specificaties

CS (snoer dikte) 3.53 mm

Hardheid 70 Shore A

ID (binnendiameter) 158.35 mm

Temperatuur Max 150 °C

Temperatuur Min -20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t