



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## Joint Torique 7.6x2.62 - ACM - 70 Shore A - Noir - ORS49550

<https://www.o-ring-stocks.eu/fr/joint-torique-7.6x2.62-acm-70-shore-a-noir-ors49550>

### Specificaties

Productnummer 49550

Merk Eurolast

Categorie ACM O-Rings

Materiaal ACM

Kleur Zwart

Kleur Black

### Basis Specificaties

Keurmerk None

Chemische Benaming PolyAcrylate Rubber / alkyl acrylate copolymer

Extra omschrijving O-ring 7.6x2.62 ACM

Maat in tekst seven comma sixty by two comma sixty two

Materiaal ACM

Merkenamen HyTemp

Omschrijving-2 O-ring ACM 7.6x2.62

Verpakkingseenheid O-ring

### Alternative maat

AS568 Maat AS 109

DIN 3771 Maat 7.6x2.62

SMS 1586 Maat 7.6 X 2.62

### Basis Specificaties

CS (snoer dikte) 2.62 mm

Hardheid 70 Shore A

ID (binnendiameter) 7.6 mm

Temperatuur Max 150 °C

Temperatuur Min -20 °C

### Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

**Minpunten**

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t