



Joint Torique 23.53x1.78 - ACM - 70 Shore A - Noir - ORS49557

<https://www.o-ring-stocks.eu/fr/joint-torique-23.53x1.78-acm-70-shore-a-noir-ors49557>

Specificaties

Productnummer	49557
Merk	Eurolast
Categorie	ACM O-Rings
Materiaal	ACM
Kleur	Zwart
Kleur	Black

Basis Specificaties

Keurmerk	None
----------	------

Chemische Benaming	PolyAcrylate Rubber / alkyl acrylate copolymer
Extra omschrijving	O-ring 23.53x1.78 ACM
Maat in tekst	twenty three comma fifty three by one comma seventy eight
Materiaal	ACM
Merknamen	HyTemp
Omschrijving-2	O-ring ACM 23.53x1.78
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 021
DIN 3771 Maat	23.53x1.78
SMS 1586 Maat	23.53 X 1.78

Basis Specificaties

CS (snoer dikte)	1.78 mm
Hardheid	70 Shore A
ID (binnendiameter)	23.53 mm
Temperatuur Max	150 °C
Temperatuur Min	-20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t