



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 227.97x6.99 - ACM - 70 Shore A - Noir - ORS49574

<https://www.o-ring-stocks.eu/fr/joint-torique-227.97x6.99-acm-70-shore-a-noir-ors49574>

Specificaties

Productnummer	49574
Merk	Eurolast
Categorie	ACM O-Rings
Materiaal	ACM
Kleur	Zwart
Kleur	Black

Basis Specificaties

Keurmerk	None
----------	------

Chemische Benaming	PolyAcrylate Rubber / alkyl acrylate copolymer
Extra omschrijving	O-ring 227.97x6.99 ACM
Maat in tekst	two hundred and twenty seven comma ninety seven by six comma ninety nine
Materiaal	ACM
Merkenamen	HyTemp
Omschrijving-2	O-ring ACM 227.97x6.99
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 447
DIN 3771 Maat	227.97x6.99
SMS 1586 Maat	227.97 X 6.99

Basis Specificaties

CS (snoer dikte)	6.99 mm
Hardheid	70 Shore A
ID (binnendiameter)	227.97 mm
Temperatuur Max	150 °C
Temperatuur Min	-20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t