



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 25.5x2.65 - FFKM - FFPM - 75 Shore A - Noir - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/fr/joint-torique-25.5x2.65-ffkm-ffpm-75-shore-a-noir-kalrez-6375-ors58576-equivalent>

Specificaties

Productnummer	58576
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart

Basis Specificaties

Keurmerk	General Purpose (+270°C)
Kleur	Black

Equivalent	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Parafluor V8910-75
------------	---

Materiaal	FFKM - FFPM
-----------	-------------

NIEUW - Details II	N894
--------------------	------

Omschrijving-2	O-ring FFKM - FFPM 25.5x2.65
----------------	------------------------------

Type Dichting	O-ring
---------------	--------

Alternative maat

DIN 3771 Maat	25.5x2.65
---------------	-----------

ISO 3601 Maat	B0255
---------------	-------

Maat in tekst	twenty five comma fifty by two comma sixty five
---------------	---

NF T 47-501 Maat	B0255
------------------	-------

SMS 1586 Maat	25.5 X 2.65
---------------	-------------

Basis Specificaties

CS (Snoer dikte)	2.65 mm
------------------	---------

Hardheid	75 Shore A
----------	------------

ID (Binnendiameter)	25.5 mm
---------------------	---------

Temperatuur Max	270 °C
-----------------	--------

Temperatuur Min	-20 °C
-----------------	--------

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
---------------------------	--------------------

Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
--------------------------------	------------------------

Specificaties

Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
Parker Parafluor® Equivalent	Parker Parafluor V8910-75
PPE Perlast® Equivalent	PPE Perlast G80A
Trellebrog Isolast® Equivalent	Trelleborg Isolast 9440

Overige Specs

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Extra omschrijving	O-ring 25.5x2.65 FFKM - FFPM
Merknamen	Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

Technische Specs

Compressieset	18,5 %
Soortelijk Gewicht	1,98 (+/- 0.04) g/cm ³
Treksterkte	18 MPa
Ultimale Rek	145 %