



O-ring-Stocks.eu - Techniparts

Rondweg 26  
8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## Joint Torique 185x4 - FFKM - FFPM - 75 Shore A - Noir - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/fr/joint-torique-185x4-ffkm-ffpm-75-shore-a-noir-kalrez-6375-ors55734-equivalent>

### Specificaties

Productnummer	55734
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart

### Basis Specificaties

Keurmerk	General Purpose (+270°C)
Kleur	Black

Equivalent	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Parafluor V8910-75
------------	---

Materiaal	FFKM - FFPM
-----------	-------------

Omschrijving-2	O-ring FFKM - FFPM 185x4
----------------	--------------------------

Type Dichting	O-ring
---------------	--------

### Alternative maat

BS1806 Maat	BS 882
-------------	--------

DIN 3771 Maat	185x4
---------------	-------

Maat in tekst	one hundred and eighty five zero by four zero
---------------	---

SMS 1586 Maat	185 X 4
---------------	---------

### Basis Specificaties

CS (Snoer dikte)	4 mm
------------------	------

Hardheid	75 Shore A
----------	------------

ID (Binnendiameter)	185 mm
---------------------	--------

Temperatuur Max	270 °C
-----------------	--------

Temperatuur Min	-20 °C
-----------------	--------

### Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
---------------------------	--------------------

Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
--------------------------------	------------------------

Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
----------------------------------	--------------------------

Parker Parafluor® Equivalent	Parker Parafluor V8910-75
------------------------------	---------------------------

**Specificaties**

PPE Perlast® Equivalent	PPE Perlast G80A
Trellebrog Isolast® Equivalent	Trelleborg Isolast 9440

**Overige Specs**

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Extra omschrijving	O-ring 185x4 FFKM - FFPM
Merknamen	Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

**Technische Specs**

Compressieset	18,5 %
Soortelijk Gewicht	1,98 (+/- 0.04) g/cm <sup>3</sup>
Treksterkte	18 MPa
Ultimale Rek	145 %