



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 19.1x2.4 - FFKM - FFPM - Haute Temp - 75 Shore A - Noir -

<https://www.o-ring-stocks.eu/fr/joint-torique-19.1x2.4-ffkm-ffpm-haute-temp-75-shore-a-noir-kalrez-4079-ors78484-equivalent>

Specificaties

Productnummer	78484
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z96
Materiaal	FFKM - FFPM
Kleur	Zwart

Basis Specificaties

Keurmerk	General Purpose (+330°C)
Kleur	Black

Equivalent	Dupont Kalrez 4079, Freudenberg Simriz 498, Greene Tweed Chemraz 615, PPE Perlast G75B, Trelleborg Isolast J8325 & Isolast J9876,
------------	---

Materiaal	FFKM - FFPM
Omschrijving-2	O-ring FFKM - FFPM 19.1x2.4
Type Dichting	O-ring

Alternative maat

DIN 3771 Maat	19.1x2.4
Maat in tekst	nineteen comma ten by two comma forty
SMS 1586 Maat	19.1 X 2.4

Basis Specificaties

CS (Snoer dikte)	2.4 mm
Hardheid	75 Shore A
ID (Binnendiameter)	19.1 mm
Temperatuur Max	330 °C
Temperatuur Min	-15 °C

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 4079
Freudenberg Simriz® Equivalent	Freudenberg Simriz 498
Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 615
Parker Parafluor® Equivalent	Not Known
PPE Perlast® Equivalent	PPE Perlast G75B

Specificaties

Trelleborg Isolast® Equivalent

Trelleborg Isolast J8325 & Isolast J9876

Overige Specs

Alternatieve benaming

FFPM – Dupont Kalrez

Chemische Benaming

Perfluoroelastomer

Extra omschrijving

O-ring 33x3.5 FFKM - FFPM

Merknamen

Kalrez® - Simriz® - Chemraz® - Spectrum® - Triazinico® - Isolast® - Parofluor® - Fluorez® - Perlast® - Perfluor®

Technische Specs

Compressieset

19,5 %

Soortelijk Gewicht

1,98 (+/- 0.03) g/cm³

Treksterkte

17,8 MPa

Ultimale Rek

152 %