



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 119,5x7 - FFKM - FFPM - Conform FDA - High Temp - 80 Shore A -

<https://www.o-ring-stocks.eu/fr/joint-torique-119.5x7-ffkm-ffpm-haute-temp-fda-ec19352004-usp-class-vi-80-shore-a-blanc-ors183692>

Specificaties

Productnummer	183692
Merk	Eurolast
Categorie	FFKM O-Rings - 80 Shore A - F808W95 - Wit
Materiaal	FFKM - FFPM
Kleur	WIT

Basis Specificaties

Keurmerk	Conform FDA - (300°C)
Kleur	White

Afmetingen	119.5x7
Equivalent	PPE Perlast G80H
Materiaal	FFKM - FFPM
Omschrijving-2	O-ring FFKM - FFPM 119.5x7
Type Dichting	O-ring

Alternative maat

DIN 3771 Maat	119.5x7
Maat in tekst	one hundred and nineteen comma fifty by seven zero
SMS 1586 Maat	119.5 X 7

Basis Specificaties

CS (Snoer dikte)	7 mm
Hardheid	80 Shore A
ID (Binnendiameter)	119.5 mm
Temperatuur Max	300 °C
Temperatuur Min	-15 °C

Equivalent aan

Dupont Kalrez® Equivalent	Not Known
Freudenberg Simriz® Equivalent	Not Known
Greene Tweed Chemraz® Equivalent	Not Known
Parker Parafluor® Equivalent	Not Known
PPE Perlast® Equivalent	PPE Perlast G80H
Trelleborg Isolast® Equivalent	Not Known

Specificaties

Overige Specs

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Extra omschrijving	O-ring 119.5x7 FFKM - FFPM
Merkmamen	Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

Technische Specs

Compressieset	28 %
Soortelijk Gewicht	2,55 (+/- 0,03) g/cm ³
Treksterkte	13,2 MPa
Ultimale Rek	100 %