



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 23.39x3.53 - FFKM - FFPM - 75 Shore A - Noir - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/fr/joint-torique-23.39x3.53-ffkm-ffpm-75-shore-a-noir-kalrez-6375-ors179273-equivalent>

Specificaties

Productnummer	179273
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F757Z75
Materiaal	FFKM - FFPM
Kleur	ZWART
Kleur	Black

Basis Specificaties

Keurmerk	None
----------	------

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Equivalent	Dupont Kalrez 6375 - Fruedenberg Simriz 495 - Greene Tweed Chemraz 605 - Parker Parafluor V8910-75 - PPE Perlast G80A - Trelleborg Isolast 9440

Extra omschrijving	O-ring 23.39x3.53 FFKM
Maat in tekst	twenty three comma thirty nine by three comma fifty three
Materiaal	FFKM - FFPM
Merkenamen	Kalrez® - Simriz® - Chemraz® - Spectrum® - Triazinico® - Isolast® - Parofluor® - Fluorez® - Perlast® - Perfluor®
Omschrijving-2	O-ring FFKM - FFPM 23.39x3.53
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 119
DIN 3771 Maat	23.39 x 3.53
SMS 1586 Maat	23.39x3.53

Basis Specificaties

CS (snoer dikte)	3.53 mm
Hardheid	75 Shore A
ID (binnendiameter)	23.39 mm
Temperatuur Max	330 °C
Temperatuur Min	-15 °C

Equivalent aan

Specificaties

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
Freudenberg Simriz® Equivalent	Fruedenberg Simriz 495
Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
Parker Parafluor® Equivalent	Parker Parafluor V8910-75
PPE Perlast® Equivalent	PPE Perlast G80A
Trellebrog Isolast® Equivalent	Trellebrog Isolast 9440