



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 37.82x1.78 - FFKM - FFPM - Haute Temp - 75 Shore A - Noir -

<https://www.o-ring-stocks.eu/fr/joint-torique-37.82x1.78-ffkm-ffpm-haute-temp-75-shore-a-noir-ors83275>

Specificaties

Productnummer	83275
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F75Z75
Materiaal	FFKM - FFPM
Kleur	Zwart
Kleur	Black

Basis Specificaties

Keurmerk	High Temperature
----------	------------------

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Equivalent	Dupont Kalrez 6375 - Fruedenberg Simriz 495 - Greene Tweed Chemraz 605 - Parker Parafluor V8910-75 - PPE Perlast G80A - Trelleborg Isolast 9440

Extra omschrijving	O-ring 90x5.7 FFKM
Maat in tekst	thirty seven comma eighty two by one comma seventy eight

Materiaal	FFKM - FFPM
Merknamen	Kalrez® - Simriz® - Chemraz® - Spectrum® - Triazinico® - Isolast® - Parofluor® - Fluorez® - Perlast® - Perfluor®

Omschrijving-2	O-ring FFKM - FFPM 37.82x1.78
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 129
DIN 3771 Maat	37.82x1.78
SMS 1586 Maat	37.82 X 1.78

Basis Specificaties

CS (snoer dikte)	1.78 mm
Hardheid	75 Shore A
ID (binnendiameter)	37.82 mm
Temperatuur Max	340 °C
Temperatuur Min	-15 °C

Specificaties

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
Freudenberg Simriz® Equivalent	Fruedenberg Simriz 495
Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
Parker Parafluor® Equivalent	Parker Parafluor V8910-75
PPE Perlast® Equivalent	PPE Perlast G80A
Trellebrog Isolast® Equivalent	Trellebrog Isolast 9440