



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

Joint Torique 47x4 - FFKM - FFPM - 75 Shore A - Noir - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/fr/joint-torique-47x4-ffkm-ffpm-75-shore-a-noir-kalrez-6375-ors55218-equivalent>

Specificaties

Productnummer	55218
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart

Basis Specificaties

Keurmerk	General Purpose (+270°C)
Kleur	Black

Equivalent	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Paraflur V8910-75
------------	--

Materiaal	FFKM - FFPM
-----------	-------------

NIEUW - Details II	N894
--------------------	------

Omschrijving-2	O-ring FFKM - FFPM 47x4
----------------	-------------------------

Type Dichting	O-ring
---------------	--------

Alternative maat

BS1806 Maat	BS 829
-------------	--------

DIN 3771 Maat	47x4
---------------	------

Maat in tekst	forty seven zero by four zero
---------------	-------------------------------

SMS 1586 Maat	47 X 4
---------------	--------

Basis Specificaties

CS (Snoer dikte)	4 mm
------------------	------

Hardheid	75 Shore A
----------	------------

ID (Binnendiameter)	47 mm
---------------------	-------

Temperatuur Max	270 °C
-----------------	--------

Temperatuur Min	-20 °C
-----------------	--------

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
---------------------------	--------------------

Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
--------------------------------	------------------------

Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
----------------------------------	--------------------------

Specificaties

Parker Parafluor® Equivalent Parker Parafluor V8910-75

PPE Perlast® Equivalent PPE Perlast G80A

Trelleborg Isolast® Equivalent Trelleborg Isolast 9440

Overige Specs

Alternatieve benaming FFPM – Dupont Kalrez

Chemische Benaming Perfluoroelastomer

Extra omschrijving O-ring 47x4 FFKM - FFPM

Merkmamen Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

Technische Specs

Compressieset 18,5 %

Soortelijk Gewicht 1,98 (+/- 0.04) g/cm³

Treksterkte 18 MPa

Ultimale Rek 145 %