



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## O-ring 9.25x1.78 - ACM - 70 Shore A - Nero - ORS35530

<https://www.o-ring-stocks.eu/it/o-ring-9.25x1.78-acm-70-shore-a-nero-ors35530>

### Specificaties

|               |             |
|---------------|-------------|
| Productnummer | 35530       |
| Merk          | Eurolast    |
| Categorie     | ACM O-Rings |
| Materiaal     | ACM         |
| Kleur         | Zwart       |
| Kleur         | Black       |

### Basis Specificaties

|          |      |
|----------|------|
| Keurmerk | None |
|----------|------|

|                    |                                                   |
|--------------------|---------------------------------------------------|
| Chemische Benaming | PolyAcrylate Rubber / alkyl acrylate copolymer    |
| Extra omschrijving | O-ring 9.25x1.78 ACM                              |
| Maat in tekst      | nine comma twenty five by one comma seventy eight |
| Materiaal          | ACM                                               |
| Merknamen          | HyTemp                                            |
| Omschrijving-2     | O-ring ACM 9.25x1.78                              |
| Verpakkingseenheid | O-ring                                            |

### Alternative maat

|               |             |
|---------------|-------------|
| AS568 Maat    | AS 012      |
| DIN 3771 Maat | 9.25x1.78   |
| SMS 1586 Maat | 9.25 X 1.78 |

### Basis Specificaties

|                     |            |
|---------------------|------------|
| CS (snoer dikte)    | 1.78 mm    |
| Hardheid            | 70 Shore A |
| ID (binnendiameter) | 9.25 mm    |
| Temperatuur Max     | 150 °C     |
| Temperatuur Min     | -20 °C     |

### Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

**Minpunten**

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t