



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 53.34x5.33 - ACM - 70 Shore A - Nero - ORS49561

<https://www.o-ring-stocks.eu/it/o-ring-53.34x5.33-acm-70-shore-a-nero-ors49561>

Specificaties

Productnummer 49561

Merk Eurolast

Categorie ACM O-Rings

Materiaal ACM

Kleur Zwart

Kleur Black

Basis Specificaties

Keurmerk None

Chemische Benaming PolyAcrylate Rubber / alkyl acrylate copolymer

Extra omschrijving O-ring 53.34x5.33 ACM

Maat in tekst fifty three comma thirty four by five comma thirty three

Materiaal ACM

Merkenamen HyTemp

Omschrijving-2 O-ring ACM 53.34x5.33

Verpakkingseenheid O-ring

Alternative maat

AS568 Maat AS 330

DIN 3771 Maat 53.34x5.33

SMS 1586 Maat 53.34 X 5.33

Basis Specificaties

CS (snoer dikte) 5.33 mm

Hardheid 70 Shore A

ID (binnendiameter) 53.34 mm

Temperatuur Max 150 °C

Temperatuur Min -20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t