



O-ring-Stocks.eu - Techniparts

Rondweg 26  
8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## O-ring 117,05x3,53 - FFKM - FFPM - Conform FDA - High Temp - 80 Shore

<https://www.o-ring-stocks.eu/it/o-ring-117.05x3.53-ffkm-ffpm-alta-temp-fda-ec19352004-usp-class-vi-80-shore-a-bianco-ors183689>

### Specificaties

Productnummer	183689
Merk	Eurolast
Categorie	FFKM O-Rings - 80 Shore A - F808W95 - Wit
Materiaal	FFKM - FFPM
Kleur	WIT

### Basis Specificaties

Keurmerk	Conform FDA - (300°C)
Kleur	White

Afmetingen	117.05x3.53
Equivalent	PPE Perlast G80H
Materiaal	FFKM - FFPM
Omschrijving-2	O-ring FFKM - FFPM 117.05x3.53
Type Dichting	O-ring

### Alternative maat

BS1806 Maat	BS 882
DIN 3771 Maat	117.05x3.53
Maat in tekst	one hundred and seventeen comma five by three comma fifty three
SMS 1586 Maat	117.05 X 3,53

### Basis Specificaties

CS (Snoer dikte)	3.53 mm
Hardheid	80 Shore A
ID (Binnendiameter)	117.05 mm
Temperatuur Max	300 °C
Temperatuur Min	-15 °C

### Equivalent aan

Dupont Kalrez® Equivalent	Not Known
Freudenberg Simriz® Equivalent	Not Known
Greene Tweed Chemraz® Equivalent	Not Known
Parker Parafluor® Equivalent	Not Known

## Specificaties

PPE Perlast® Equivalent PPE Perlast G80H

Trelleborg Isolast® Equivalent Not Known

## Overige Specs

Alternatieve benaming FFPM – Dupont Kalrez

Chemische Benaming Perfluoroelastomer

Extra omschrijving O-ring 117.05x3.53 FFKM - FFPM

Merkmamen Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

## Technische Specs

Compressieset 28 %

Soortelijk Gewicht 2,55 (+/- 0,03) g/cm<sup>3</sup>

Treksterkte 13,2 MPa

Ultimale Rek 100 %