



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

<https://www.o-ring-stocks.eu/it/o-ring-99.39x4.36-ffkm-ffpm-75-shore-a-nero-kalrez-6375-ors61520-equivalente>

Specificaties

Productnummer	61520
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart

Basis Specificaties

Keurmerk	General Purpose (+270°C)
Kleur	Black

Equivalent	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Parafluor V8910-75
Materiaal	FFKM - FFPM
NIEUW - Details II	N894
Omschrijving-2	O-ring FFKM - FFPM 99.39x4.36
Type Dichting	O-ring

Alternative maat

DIN 3771 Maat	99.39x4.36
Maat in tekst	ninety nine comma thirty nine by four comma thirty six
SMS 1586 Maat	99.39 X 4.36

Basis Specificaties

CS (Snoer dikte)	4.36 mm
Hardheid	75 Shore A
ID (Binnendiameter)	99.39 mm
Temperatuur Max	270 °C
Temperatuur Min	-20 °C

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
Parker Parafluor® Equivalent	Parker Parafluor V8910-75
PPE Perlast® Equivalent	PPE Perlast G80A

Specificaties

Trelleborg Isolast® Equivalent

Trelleborg Isolast 9440

Overige Specs

Alternatieve benaming

FFPM – Dupont Kalrez

Chemische Benaming

Perfluoroelastomer

Extra omschrijving

O-ring 99.39x4.36 FFKM - FFPM

Merkmamen

Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum -
Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® -
HPSealing® - Perfluor® - Polymax

Technische Specs

Compressieset

18,5 %

Soortelijk Gewicht

1,98 (+/- 0.04) g/cm³

Treksterkte

18 MPa

Ultimale Rek

145 %