



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 20.22x3.53 - ACM - 70 Shore A - Zwart - ORS35507

<https://www.o-ring-stocks.eu/nl/o-ring-20.22x3.53-acm-70-shore-a-zwart-ors35507>

Specificaties

Productnummer	35507
Merk	Eurolast
Categorie	ACM O-Rings
Materiaal	ACM
Kleur	Zwart
Kleur	Black

Basis Specificaties

Keurmerk	None
----------	------

Chemische Benaming	PolyAcrylate Rubber / alkyl acrylate copolymer
Extra omschrijving	O-ring 20.22x3.53 ACM
Maat in tekst	twenty comma twenty two by three comma fifty three
Materiaal	ACM
Merknamen	HyTemp
Omschrijving-2	O-ring ACM 20.22x3.53
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 211
DIN 3771 Maat	20.22x3.53
SMS 1586 Maat	20.22 X 3.53

Basis Specificaties

CS (snoer dikte)	3.53 mm
Hardheid	70 Shore A
ID (binnendiameter)	20.22 mm
Temperatuur Max	150 °C
Temperatuur Min	-20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t