



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 317x7 - FFKM - FFPM - 90 Shore A - Zwart - ORS188945

<https://www.o-ring-stocks.eu/nl/o-ring-317x7-ffkm-ffpm-90-shore-a-zwart-ors188945>

Specificaties

| | |
|---------------|-------------------------------------|
| Productnummer | 188945 |
| Merk | Eurolast |
| Categorie | FFKM O-Rings - 90 Shore A - F909Z93 |
| Materiaal | FFKM - FFPM |
| Kleur | ZWART |

Basis Specificaties

| | |
|----------|-------|
| Keurmerk | None |
| Kleur | Black |

| | |
|----------------|--------------------------|
| Afmetingen | 317x7 |
| Equivalent | Not Known |
| Materiaal | FFKM - FFPM |
| Omschrijving-2 | O-ring FFKM - FFPM 317x7 |
| Type Dichting | O-ring |

Alternative maat

| | |
|---------------|--|
| DIN 3771 Maat | 317x7 |
| Maat in tekst | three hundred and seventeen zero by seven zero |
| SMS 1586 Maat | 317 X 7 |

Basis Specificaties

| | |
|---------------------|------------|
| CS (Snoer dikte) | 7 mm |
| Hardheid | 90 Shore A |
| ID (Binnendiameter) | 317 mm |
| Temperatuur Max | 270 °C |
| Temperatuur Min | -20 °C |

Equivalent aan

| | |
|----------------------------------|-----------|
| Dupont Kalrez® Equivalent | Not Known |
| Freudenberg Simriz® Equivalent | Not Known |
| Greene Tweed Chemraz® Equivalent | Not Known |
| Parker Parafluor® Equivalent | Not Known |
| PPE Perlast® Equivalent | Not Known |
| Trelleborg Isolast® Equivalent | Not Known |

Specificaties

Overige Specs

| | |
|-----------------------|--|
| Alternatieve benaming | FFPM – Dupont Kalrez |
| Chemische Benaming | Perfluoroelastomer |
| Extra omschrijving | O-ring 317x7 FFKM - FFPM |
| Merknamen | Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax |

Technische Specs

| | |
|--------------------|-----------------------------------|
| Compressieset | 19 % |
| Soortelijk Gewicht | 1,98 (+/- 0,04) g/cm ³ |
| Treksterkte | 18,5 MPa |
| Ultimale Rek | 110 % |