



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 33x2.62 - FFKM - FFPM - Stoom - Heet Water - 75 Shore A - Zwart -

<https://www.o-ring-stocks.eu/nl/o-ring-33x2.62-ffkm-ffpm-stoom-heet-water-75-shore-a-zwart-kalrez-1050lf-ors107701-equivalent>

Specificaties

Productnummer	107701
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758ZSR
Materiaal	FFKM - FFPM
Kleur	Zwart
Kleur	Black

Basis Specificaties

Keurmerk	Steam. Hot Water
----------	------------------

Alternatieve benaming	FFPM – Dupont Kalrez
Chemische Benaming	Perfluoroelastomer
Equivalent	Kalrez® 1050LF . Chemraz® 555 . Chemraz® 605 . Perflour® V8545-75 . Simriz® 487 . Isolast® J9512 . Polymax P300B8ST . Evolast N8SR

Extra omschrijving	O-ring 33x2.62 FFKM
Maat in tekst	thirty three zero by two comma sixty two
Materiaal	FFKM - FFPM
Merknamen	Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax
Omschrijving-2	O-ring FFKM - FFPM 33x2.62
Verpakkingseenheid	O-ring

Alternative maat

AS568 Maat	AS 125
DIN 3771 Maat	33x2.62
SMS 1586 Maat	33 X 2.62

Basis Specificaties

CS (snoer dikte)	2.62 mm
Hardheid	75 Shore A
ID (binnendiameter)	33 mm
Temperatuur Max	330 °C
Temperatuur Min	-15 °C