



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 164.47x5.33 - FFKM - FFPM - 75 Shore A - Zwart - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/nl/o-ring-164.47x5.33-ffkm-ffpm-75-shore-a-zwart-kalrez-6375-ors51222-equivalent>

Specificaties

Productnummer	51222
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart

Basis Specificaties

Keurmerk	General Purpose (+270°C)
Kleur	Black

Equivalent	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Parafluor V8910-75
------------	---

Materiaal	FFKM - FFPM
-----------	-------------

NIEUW - Details II	N894
--------------------	------

Omschrijving-2	O-ring FFKM - FFPM 164.47x5.33
----------------	--------------------------------

Type Dichting	O-ring
---------------	--------

Alternative maat

AS568 Maat	AS 439
------------	--------

DIN 3771 Maat	164.47x5.33
---------------	-------------

Maat in tekst	one hundred and sixty four comma forty seven by five comma thirty three
---------------	---

SMS 1586 Maat	164.47 X 5.33
---------------	---------------

Basis Specificaties

CS (Snoer dikte)	5.33 mm
------------------	---------

Hardheid	75 Shore A
----------	------------

ID (Binnendiameter)	164.47 mm
---------------------	-----------

Temperatuur Max	270 °C
-----------------	--------

Temperatuur Min	-20 °C
-----------------	--------

Equivalent aan

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
---------------------------	--------------------

Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
--------------------------------	------------------------

Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
----------------------------------	--------------------------

Specificaties

Parker Parafluor® Equivalent

Parker Parafluor V8910-75

PPE Perlast® Equivalent

PPE Perlast G80A

Trelleborg Isolast® Equivalent

Trelleborg Isolast 9440

Overige Specs

Alternatieve benaming

FFPM – Dupont Kalrez

Chemische Benaming

Perfluoroelastomer

Extra omschrijving

O-ring 164.47x5.33 FFKM - FFPM

Merkmamen

Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum -
Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® -
HPSealing® - Perfluor® - Polymax**Technische Specs**

Compressieset

18,5 %

Soortelijk Gewicht

1,98 (+/- 0.04) g/cm³

Treksterkte

18 MPa

Ultimale Rek

145 %