



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 304.39x3.53 - ACM - 70 Shore A - Black - ORS35519

<https://www.o-ring-stocks.eu/o-ring-304.39x3.53-acm-70-shore-a-black-ors35519>

Specificaties

Productnummer	35519
Merk	Eurolast
Categorie	ACM O-Rings
Materiaal	ACM
Kleur	Zwart
Color	Black

Core Spec's

Approval	None
----------	------

Chemical Name	PolyAcrylate Rubber / alkyl acrylate copolymer
Description 2	O-ring ACM 304.39x3.53
Material	ACM
Packaging Unit	O-ring
Product name	O-ring 304.39x3.53 ACM
Size in text	three hundred and four comma thirty nine by three comma fifty three
Trade names	HyTemp

Alternative Size

AS568 Size Chart	AS 278
DIN 3771 Size Chart	304.39x3.53
SMS 1586 Size chart	304.39 X 3.53

Core Spec's

CS (Cross Section)	3.53 mm
Hardness	70 Shore A
ID (inner diameter)	304.39 mm
Temperature Max	150 °C
Temperature Min	-20 °C

Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

Minpunten

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t