



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## O-ring 7.6x2.62 - ACM - 70 Shore A - Black - ORS49550

<https://www.o-ring-stocks.eu/o-ring-7.6x2.62-acm-70-shore-a-black-ors49550>

### Specificaties

|               |             |
|---------------|-------------|
| Productnummer | 49550       |
| Merk          | Eurolast    |
| Categorie     | ACM O-Rings |
| Materiaal     | ACM         |
| Kleur         | Zwart       |
| Color         | Black       |

### Core Spec's

|          |      |
|----------|------|
| Approval | None |
|----------|------|

|                |                                                |
|----------------|------------------------------------------------|
| Chemical Name  | PolyAcrylate Rubber / alkyl acrylate copolymer |
| Description 2  | O-ring ACM 7.6x2.62                            |
| Material       | ACM                                            |
| Packaging Unit | O-ring                                         |
| Product name   | O-ring 7.6x2.62 ACM                            |
| Size in text   | seven comma sixty by two comma sixty two       |
| Trade names    | HyTemp                                         |

### Alternative Size

|                     |            |
|---------------------|------------|
| AS568 Size Chart    | AS 109     |
| DIN 3771 Size Chart | 7.6x2.62   |
| SMS 1586 Size chart | 7.6 X 2.62 |

### Core Spec's

|                     |            |
|---------------------|------------|
| CS (Cross Section)  | 2.62 mm    |
| Hardness            | 70 Shore A |
| ID (inner diameter) | 7.6 mm     |
| Temperature Max     | 150 °C     |
| Temperature Min     | -20 °C     |

### Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

**Minpunten**

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t