



O-ring-Stocks.eu - Techniparts

Rondweg 26

8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## O-ring 196.44x3.53 - ACM - 70 Shore A - Black - ORS49573

<https://www.o-ring-stocks.eu/o-ring-196.44x3.53-acm-70-shore-a-black-ors49573>

### Specificaties

Productnummer	49573
Merk	Eurolast
Categorie	ACM O-Rings
Materiaal	ACM
Kleur	Zwart
Color	Black

### Core Spec's

Approval	None
----------	------

Chemical Name	PolyAcrylate Rubber / alkyl acrylate copolymer
Description 2	O-ring ACM 196.44x3.53
Material	ACM
Packaging Unit	O-ring
Product name	O-ring 196.44x3.53 ACM
Size in text	one hundred and ninety six comma forty four by three comma fifty three
Trade names	HyTemp

### Alternative Size

AS568 Size Chart	AS 265
DIN 3771 Size Chart	196.44x3.53
SMS 1586 Size chart	196.44 X 3.53

### Core Spec's

CS (Cross Section)	3.53 mm
Hardness	70 Shore A
ID (inner diameter)	196.44 mm
Temperature Max	150 °C
Temperature Min	-20 °C

### Pluspunten

+ Resistance to petroleum fuels and oils, automatic transmission fluid, type A power steering fluid. Good resistance to mineral oil, sunlight, oxygen, and ozone.

**Minpunten**

- Cannot be used in alcohol, alkalis, glycol based brake fluids, EP fluids, chlorinated hydrocarbons, gear oils, glycol based brake fluids, hydrocarbons, water or steam (above 275°F), acids and amines. Lower water compatibility, cold flexibility, strength, and compression set resistance t