



O-ring-Stocks.eu - Techniparts

Rondweg 26  
8091XB, Wezep

E-MAIL [info@o-ring-stocks.eu](mailto:info@o-ring-stocks.eu)

TEL +31382024043

KVK 08174024

## O-ring 37.7x3.5 - FFKM - FFPM - 90 Shore A - Black - ORS188858

<https://www.o-ring-stocks.eu/o-ring-37.7x3.5-ffkm-ffpm-90-shore-a-black-ors188858>

### Specificaties

Productnummer	188858
Merk	Eurolast
Categorie	FFKM O-Rings - 90 Shore A - F909Z93
Materiaal	FFKM - FFPM
Kleur	ZWART
<b>Core Spec's</b>	
Approval	None
Color	Black

Description 2	O-ring FFKM - FFPM 37.7x3.5
Dimensions	37.7x3.5
Equal to	Not Known
Material	FFKM - FFPM
Seal type	O-ring

### Alternative Size

DIN 3771 Size Chart	37.7x3.5
JIS B 2401 Size Chart	JIS P38
Size in text	thirty seven comma seventy by three comma fifty
SMS 1586 Size chart	37.7 X 3.5

### Core Spec's

CS (Cross Section)	3.5 mm
Hardness	90 Shore A
ID (Inner diameter)	37.7 mm
Temperature Max	270 °C
Temperature Min	-20 °C

### Technical Spec's

Compression Set	19 %
-----------------	------

### Engels: Technical Specifications

Specific Gravity	1,98 (+/- 0,04) g/cm3
------------------	-----------------------

### Equivalent to

Dupont Kalrez® Equivalent	Not Known
---------------------------	-----------

**Specificaties**

Freudenberg Simriz® Equivalent	Not Known
Greene Tweed Chemraz® Equivalent	Not Known
Parker Parafluor® Equivalent	Not Known
Precision Polymer Engineering Perlast® Equivalent	Not Known
Trelleborg Isolast® Equivalent	Not Known

**Other Specs**

Alternative names	FFPM – Dupont Kalrez
Chemical Name	Perfluoroelastomer
Product name	O-ring 37.7x3.5 FFKM - FFPM
Trade names	Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

**Technical Specifications**

Tensile Strength	18,5 MPa
Ultimate Elongation	110 %