



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 481.46x5.33 - FFKM - FFPM - 90 Shore A - Black - ORS99673

<https://www.o-ring-stocks.eu/o-ring-481.46x5.33-ffkm-ffpm-90-shore-a-black-ors99673>

Specificaties

Productnummer	99673
Merk	Eurolast
Categorie	FFKM O-Rings - 90 Shore A - F909Z93
Materiaal	FFKM - FFPM
Kleur	Zwart
Core Spec's	
Approval	None
Color	Black

Description 2	O-ring FFKM - FFPM 481.46x5.33
Dimensions	481.46x5.33
Equal to	Not Known
Material	FFKM - FFPM
Seal type	O-ring

Alternative Size

AS568 Size Chart	AS 142
DIN 3771 Size Chart	481.46x5.33
Size in text	four hundred and eighty one comma forty six by five comma thirty three
SMS 1586 Size chart	481.46 X 5.33

Core Spec's

CS (Cross Section)	5.33 mm
Hardness	90 Shore A
ID (Inner diameter)	481.46 mm
Temperature Max	270 °C
Temperature Min	-20 °C

Technical Spec's

Compression Set	19 %
-----------------	------

Engels: Technical Specifications

Specific Gravity	1,98 (+/- 0,04) g/cm3
------------------	-----------------------

Equivalent to

Specificaties

Dupont Kalrez® Equivalent	Not Known
Freudenberg Simriz® Equivalent	Not Known
Greene Tweed Chemraz® Equivalent	Not Known
Parker Parafluor® Equivalent	Not Known
Precision Polymer Engineering Perlast® Equivalent	Not Known
Trelleborg Isolast® Equivalent	Not Known

Other Specs

Alternative names	FFPM – Dupont Kalrez
Chemical Name	Perfluoroelastomer
Product name	O-ring 481.46x5.33 FFKM - FFPM
Trade names	Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

Technical Specifications

Tensile Strength	18,5 MPa
Ultimate Elongation	110 %