



O-ring-Stocks.eu - Techniparts

Rondweg 26
8091XB, Wezep

E-MAIL info@o-ring-stocks.eu

TEL +31382024043

KVK 08174024

O-ring 485x4 - FFKM - FFPM - 75 Shore A - Black - Kalrez® 6375 -

<https://www.o-ring-stocks.eu/o-ring-485x4-ffkm-ffpm-75-shore-a-black-kalrez-6375-ors65636-equivalent>

Specificaties

Productnummer	65636
Merk	Eurolast
Categorie	FFKM O-Rings - 75 Shore A - F758Z94
Materiaal	FFKM - FFPM
Kleur	Zwart
Core Spec's	
Approval	General Purpose (+270°C)
Color	Black

Description 2	O-ring FFKM - FFPM 485x4
Equal to	Dupont Kalrez 6375, Freudenberg Simriz 495, Greene Tweed Chemraz 605, PPE Perlast G80A, Parker Paraflur V8910-75
Material	FFKM - FFPM
Seal type	O-ring

Alternative Size

DIN 3771 Size Chart	485x4
Size in text	four hundred and eighty five zero by four zero
SMS 1586 Size chart	485 X 4

Core Spec's

CS (Cross Section)	4 mm
Hardness	75 Shore A
ID (Inner diameter)	485 mm
Temperature Max	270 °C
Temperature Min	-20 °C

Technical Spec's

Compression Set	18,5 %
-----------------	--------

Engels: Technical Specifications

Specific Gravity	1,98 (+/- 0.04) g/cm ³
------------------	-----------------------------------

Equivalent to

Dupont Kalrez® Equivalent	Dupont Kalrez 6375
---------------------------	--------------------

Specificaties

Freudenberg Simriz® Equivalent	Freudenberg Simriz 495
Greene Tweed Chemraz® Equivalent	Greene Tweed Chemraz 605
Parker Parafluor® Equivalent	Parker Parafluor V8910-75
Precision Polymer Engineering Perlast® Equivalent	PPE Perlast G80A
Trelleborg Isolast® Equivalent	Trelleborg Isolast 9440

Other Specs

Alternative names	FFPM – Dupont Kalrez
Chemical Name	Perfluoroelastomer
Product name	O-ring 485x4 FFKM - FFPM
Trade names	Evolast® - Chemraz® - Simriz® - Kalrez® - Spectrum - Triazinico - Isolast® - Parofluor® - Fluorez - Perlast® - HPSealing® - Perfluor® - Polymax

Technical Specifications

Tensile Strength	18 MPa
Ultimate Elongation	145 %